

Reverse Glenoid Rocking Horse Evaluation of the TITAN™ Reverse Shoulder System using ASTM F2028

Marc Taylor¹, Erik Woodard¹, & Andy Whitten¹

¹Smith & Nephew, Inc., Memphis, TN
marc.taylor@smith-nephew.com

Disclosures: Marc Taylor (3a, 4 - Smith & Nephew, Inc.), Erik Woodard (3a – Smith & Nephew, Inc.), Andy Whitten (3a, 4 – Smith & Nephew, Inc.)

INTRODUCTION: Reverse total shoulder arthroplasty has seen an increase in use and expanded indications over the last 20 years. Such indications now include glenoid bone loss or deformity, treatment of severe osteoarthritis, rheumatoid arthritis, proximal humeral fractures, and failed arthroplasty. High failure rates were observed in early reverse total shoulder arthroplasty due to glenoid baseplate loosening [1]. The goal of this study was to investigate the resistance of a reverse shoulder glenoid baseplate (TITAN™ Reverse Shoulder System) to loosening, as compared to competitive devices at an increased cycle count compared to the current relevant standard guidance. The TITAN™ System included a curved baseplate (TCB). The competitive devices included an augmented baseplate (AB) and a flat-backed baseplate (FBB). All devices were evaluated using a reverse glenoid rocking horse test as outlined in ASTM F2028.

METHODS: The testing protocol was established based on the recommendations of ASTM F2028-17 and guidance from the FDA [2]. Constructs consisted of a foam block, baseplate, screws, glenosphere, and poly insert. A minimum of three constructs were tested for each design. Constructs were assembled following the recommended surgical technique of each manufacturer. To have a worst-case comparison between designs, the number, length, and orientation of the screws for each construct was chosen based on the minimum requirements outlined in each specific surgical technique. Pre-fatigue displacement measurements were collected by applying a shear load of 350 ± 15 N parallel to the glenoid plane as an axial compressive load of 430 ± 15 N was applied perpendicular to the glenoid plane, approximately through the center of rotation of the glenosphere (Figure 1). The shear and compressive loads were applied at different rates so that the target loads for each direction were achieved at approximately the same time. Using LVDTs, the initial pre-cyclic loading displacement of the glenoid construct was measured in the directions of both the applied shear and axial compressive load. The process was repeated for a total of three displacement measurement sets for each construct in each direction. Upon completion of the pre-fatigue displacement measurements, an axial compressive load of 750 ± 15 N was applied to the back of the humeral liner through the center of rotation (Figure 2). The glenoid construct was rotated $\pm 22.5^\circ$ about the humeral liner along the superior-inferior axis for 100,000 cycles at a rate of 1 Hz. Testing was conducted in air, at room temperature; surface lubricant was applied to the interface of the glenosphere and liner. An air-cooling jet was used to keep the humeral liner from overheating during the cyclic loading. Testing was terminated if the construct dislocated, disassociated, or failed in any way. The post-fatigue displacement measurements were performed following the same methods as the pre-fatigue measurements.

Eight total displacement measurements (average \pm standard deviation) were reported for each construct design: horizontal (shear) and vertical displacement in the superior/inferior and anterior/posterior direction before and after fatigue testing. The three repeated static measurements were averaged for each construct. The three sample means were then averaged for each design. Construct displacement results were analyzed for variance using Levene's test for equality of variances, and a one-way ANOVA with a Tukey's post-hoc test for comparison of the means ($\alpha = 0.05$).

RESULTS: Results for the pre- and post-fatigue displacement measurements are shown graphically in Figure 3. The differences between the pre-fatigue displacement measurements for the TCB constructs were statistically significant as compared to the AB constructs ($p < 0.05$); the TCB constructs had lower average displacement values. There were no statistically significant differences between three of the pre-fatigue displacement measurements for the TCB constructs as compared to the FBB constructs ($p > 0.05$). There was a statistically significant difference ($p < 0.05$) for the Horizontal SI displacement measurement. The TCB constructs had lower average displacement values as compared to the FBB constructs for all four measurement groups. All tested constructs completed 100,000 cycles of fatigue testing with no signs of disassociation between the baseplate and the foam block, no signs of disassociation between the glenosphere and the baseplate, and no fracture of the baseplate or screws. The differences between three of the post-fatigue displacement measurements for the TCB constructs were shown to be statistically significant as compared to the AB constructs ($p < 0.05$); the TCB constructs had lower average displacement values. There was a statistically significant difference ($p < 0.05$) for the Horizontal SI displacement measurement. There were no statistically significant differences between the post-fatigue displacement measurements for the TCB constructs as compared to the FBB constructs ($p > 0.05$).

DISCUSSION: One difference between the method used in this study compared to the ASTM standard was the cycle count. ASTM F2028 recommends the use of 10,000 cycles, whereas the FDA recommends a higher cycle count due to the current trends in the use of reverse shoulder arthroplasty [2]. The standard cycle count was considered justified as the test does not simulate prosthesis wear related failure modes, high-load activities are less likely with the reverse shoulder, and because the reverse glenoid component is uncemented. The higher 100,000 cycle endpoint could represent roughly 25 higher-load activities per day over a 10-year period; it resulted in a clear differentiation in displacement measurements in the reverse shoulder glenoid constructs used in this study.

SIGNIFICANCE/CLINICAL RELEVANCE: Early glenoid baseplate loosening is a known issue for reverse shoulder systems. The use of the TITAN™ Reverse Shoulder design has been demonstrated to resist glenoid baseplate loosening as compared to existing clinically available baseplate designs using a method intended to simulate physiological loading conditions typical of a reverse shoulder replacement.

REFERENCES: [1] Schell, *et al. J Shoulder Elbow Surg* (2023) 32, 1584-1593.

[2] https://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfStandards/detail.cfm?standard_identification_no=41415 (last accessed August 2023)

